

In re: Roger E. Marchant
Application No.: 10/823,218
Page 2 of 5

IN THE CLAIMS:

1-8 (canceled)

9. (currently amended) A method of reducing the thrombogenicity of a hydrophobic surface of a ~~substrate~~: substrate comprising:

- a) providing a comblike surfactant polymer comprising:
 - i) a polymeric backbone of repeating monomeric units,
 - ii) a plurality of hydrophobic side chains comprising from about 2 to about 18 methylene groups, said plurality of hydrophobic side chains being linked to said polymeric backbone by ester linkages, secondary amine linkages, amide linkages; or combinations thereof and
 - iii) a plurality of hydrophilic side chains linked to said polymeric backbone by ester linkages, secondary amine linkages, amide linkages, or combinations thereof; said hydrophilic side chains selected from the group consisting of: neutral oligosaccharide side chains having a weight average molecular weight of less than 7000; charged oligosaccharide side chains having a weight average molecular weight of less than 10,000, polyethylene oxide; and combinations thereof,

b) attaching the comblike surfactant polymer to the hydrophobic substrate to provide a substrate with reduced thrombogenicity.

10. (original) The method of claim 9 wherein said surfactant polymer is attached to said surface by immersing said surface into an aqueous solution containing said surfactant polymer.

11. (original) A method of promoting attachment of endothelial cells to the surface of a hydrophobic surface comprising:

- a) providing a comblike surfactant polymer comprising:
 - i) a polymeric backbone of repeating monomeric units,
 - ii) a plurality of hydrophobic side chains comprising from about 2 to about 18 methylene groups, said plurality of hydrophobic side chains being linked to said

In re: Roger E. Marchant
Application No.: 10/823,218
Page 3 of 5

polymeric backbone by secondary amine linkages, amide linkages; or combinations thereof and

iii) a plurality of hydrophilic side chains linked to said polymeric backbone by secondary amine linkages said hydrophilic side chains comprising an oligopeptide of from about 3 to 30 amino acid residues and having an amino acid sequence which interacts with protein receptors on the surface of endothelial cells

b) attaching the comblike surfactant polymer to the hydrophobic substrate.

12. (currently amended) The method of claim 11 wherein said oligopeptide side chains comprise an amino acid sequence selected from the group consisting of: SEQ ID NO: 1 (RGD), SEQ ID NO: 4 (RRAR), SEQ ID NO: 5 (RRRKRR), SEQ ID NO: 6 (PPRRARVT), and SEQ ID NO: 7 (~~PPREVVPRPR~~ PPREVVPRPRP).

13-15 (canceled)

16: (original) A method of preparing a surfactant polymer for changing the surface properties of a biomaterial comprising the following steps:

a) providing a polymer comprising a plurality of side groups selected from the group consisting of OH groups, COOH groups and NH₂ groups;

b) reacting said polymer with

i) an alkanoyl or an alkanal having an end for reacting with the side groups of said polymer; and

ii) a hydrophilic compound selected from the group consisting of neutral oligosaccharide chains having an end for reacting with the side groups of said polymer, charged oligosaccharide chains having an end for reacting with the side groups of said polymer, oligopeptides having an end for reacting with the side groups of said polymer, and combinations thereof;

wherein said alkanal and said alkanoyl comprise from 2 to 18 methylene groups;

wherein said neutral oligosaccharide chains have a weight average molecular weight of less than 7000;

In re: Roger E. Marchant
Application No.: 10/823,218
Page 4 of 5

wherein said charged oligosaccharide chains have a weight average molecular weight of less than 10,000; and

wherein said oligopeptides comprise from about 3 to 30 amino acid residues and a sequence which interact with protein receptors on the surface of endothelial cells.

17. (original) The method of claim 16 wherein said polymer is selected from the group consisting of poly(vinyl amine), poly(vinyl alcohol), and poly(lysine).
18. (original) The method of claim 16 wherein said polymer is simultaneously reacted with said alkanal or said alkanoyl and said hydrophilic compound.
- 19.: (original) The method of claim 16 wherein the molar feed ratio of said hydrophilic compound to said alkanal or said alkanoyl is from 3:1 to 1:6.
20. (original) The method of claim 16 further comprising the step of capping any unreacted amine groups.